

DYEACID COLORS ON NYLON	Dyeing depth(% o.w.f.)	Color fastness					
		Light	Washing		Perspiration		Water
			Color Change	Color Stain	Acid	Alkaline	
Black 2BL	2.0	5	4	4	4	4	4
Black FG	2.0	4	4	4	4-5	4-5	4
Black FG S/P	2.0	4	4	4	4-5	4-5	4
Black GL	2.0	5	4	3-4	4-5	5	4
Black MD H/C	2.0	6	4-5	4	5	5	4-5
Black MR	2.0	6	4-5	4	5	5	4-5
Blue 2R	2.0	5-6	5	5	4-5	5	4-5
Blue 2RN	1.0	6	4-5	4-5	5	5	4
Blue A2G	1.0	5	3	3-4	4	4	3
Blue AFN	1.0	4-5	4	4	3	4	4
Blue BLACK 10B	1.0	5-6	4-5	4	5	5	4
Blue GLF	1.0	6	5	4-5	4-5	4-5	4
Blue K_4R	0.2	6	4-5	4-5	4-5	4	4
Blue RL	1.0	5	4	3-4	4	4	3-4
Bordex B	2.0	5-6	5	4-5	4-5	5	4-5
Cyanine 5R New	1.0	5	4-5	4-5	5	5	4
Cyanine 6B	1.0	3	3-4	5	5	5	4
D/Green BN	1.0	3-4	4	3-4	4	4	3-4
Dark Green M-B	2.0	5	4-5	4	4-5	4-5	5
Green GSL	1.0	5	4	3-4	4	4	4
Navy R	2.0	6	5	5	5	5	5
Orange GS	1.0	3	4	4-5	4	4	4-5
Orange SLF	1.0	5-6	4-5	4	4-5	4	4
Red 2B	2.0	5	4	4-5	4-5	5	4
Red 3G	1.0	4	4-5	4-5	4-5	4-5	4
Red Brown V	1.0	5	4-5	5	4-5	4-5	4
Red GSN	1.0	4	5	4-5	5	5	4-5
Red K-2B	0.2	6-7	4-5	4	4-5	4-5	4-5
Red NG	1.0	3	4	4-5	4	4	4-5

DYEACID COLORS ON NYLON	Dyeing depth(% o.w.f.)	Color fastness					
		Light	Washing		Perspiration		Water
			Color Change	Color Stain	Acid	Alkaline	
Rubine 5BLF	1.0	6	4-5	4	4-5	4	4
Sky Blue R 200%	1.0	6	5	5	5	4-5	4-5
Violet 10B	1.0	4	4-5	4-5	5	5	4
Violet FBL	1.0	5	5	4-5	4-5	4-5	4
Yellow 2R	2.0	6-7	5	5	4	5	4-5
Yellow 3RL	1.0	4	4	4	5	4	4
Yellow 4G	2.0	6	5	5	4	5	4-5
Yellow 5GW	1.0	6	5-6	5	5-6	5	5
Yellow A4R	1.0	5-6	4-5	4	4	4	4
Yellow K-4R	0.2	6	5-6	4-5	5	4	4-5
Yellow MR	1.0	3-4	4	4	4	4	4